

Flexan corporation

E8607

Typical Physicals

Durometer	61
Modulus, 100% (psi)	250
Modulus, 200% (psi)	660
Modulus, 300% (psi)	1470
Tensile (psi)	2200
Elongation (%)	400
Tear (pli)	210

Compression Set, 22 hrs/100 °C

Solid (%)	6.5
Plied (%)	11.3